

Viva



FIRE
RETARDANT



ANTI
MICROBIAL




ANTI
MILDEW




ANTI
UV

Digital Color Card



NV-2701



NV-2710



NV-2702



NV-2703




NV-2704



NV-2705




NV-2706



NV-2707



NV-2708



NV-2709

SPECIFICATIONS

Composition : PVC & Knitted Polyester
 Special Surface Finish : Fabric Look
 Thickness : 1.20 mm
 Width : 137 cm
 Usage : Indoor & Outdoor Upholstery

PERFORMANCE

Abrasion : 30.000 rubs
 Flammability : CA-117
 Anti Microbial : ASTM G-21
 Anti Mildew : ATCC 147
 UV Resistant : ASTM G154

APPLICATIONS



SOFA



BAG



STATIONERY

*Colors shown are indicative references only and will vary dependent on screen resolution

NUVRINO
artistic synthetic leather

www.nuvrino.com

HEAD OFFICE : PT. BERKAT UNGGUL PRATAMA

Komplek Citta Graha, Jl. Panjang No. 26 Blok 2L | Jakarta 11520 - Indonesia | +62 21 5819089

SHOWROOM : LEDER HAUS

JAKARTA • Komplek Cipete Square, Jl. Cipete Raya 55 No.7 | Jakarta 12410 - Indonesia | +62 21 75900 679

BANDUNG • Komplek Batununggal Indah, Jl. Batununggal Indah Raya No. 415 | Bandung 40266 - Indonesia | +62 22 8730 7759

BALI • Komplek Istana Kuta Galeria, Jl. Patih Jelantik, Blok PM1 No.6 | Kuta, Badung, Bali 80361 - Indonesia | +62361 4752 806

Test Report

Report No.: YJ2020110115

Page 2 of 3

I. Test Conducted

This test was conducted in accordance with CA TB 117-2013 Requirements, Test Procedure and Apparatus for Testing the Smolder Resistance of Materials Used in Upholstered Furniture, Section 1: Cover fabric test.

II. Sample Details

Description	Fabric		
Color	Blue	Area density	About 589 g/m ²
Sample size	203 mm×203 mm, 3 pcs; 203 mm×381 mm, 3 pcs		

III. Traceability Record

1. Conditioning

Temperature	23.3 °C	Relative Humidity	53 % R.H.
Start Time	Nov. 19, 2020	End time	Nov. 24, 2020

IV. Test Results

Test Items	Specimen 1	Specimen 2	Specimen 3	Comment
Obvious ignition	No	No	No	Pass
Smolder more than 45 min	No	No	No	
Vertical char length(mm)	10.0	10.0	12.5	

V. Pass/fail criteria

- A single mock-up test specimen fails to meet the requirements of this test procedure if any of the following criteria occurs:
 - The mock-up test specimen continues to smolder after the 45 minute test duration;
 - A vertical char length of more than 1.8 inches (45 mm) develops on the cover fabric.
 - The mock-up test specimen transitions to open flaming.
- The cover fabric passes the test if three initial mock-up specimens pass the test, i.e., the cigarettes burn their full length and the mock-ups are no longer smoldering.
- If more than one initial specimen fails, the cover fabric fails the test.
- If any one of the three initial specimens fails, repeat the test on additional three specimens.
- If all three additional specimens pass the test, the cover fabric passes the test. If any one of the additional three specimens fails, the cover fabric fails the test.

The test report shall only be used for client scientific research, teaching, internal quality control, product research and development, etc... and just for client internal reference.



Test Report

Report No.: YJ2020110115

Page 3 of 3

Photo Appendix



*** End of Report ***

Statement

1. This report is considered invalid without approved signature, special seal and the seal on the perforation;
2. The sample(s) and sample information was/were provided by the client who should be responsible for the authenticity which CTI-FST hasn't verified;
3. The result(s) shown in this report refer(s) only to the sample(s) tested;
4. Without written approval of CTI-FST, this report can't be reproduced except in full.



TEST REPORT

APPLICANT : PT. BERKAT UNGGUL PRATAMA
KOMPLEK CITTA GRAHA
JL. PANJANG NO. 26 BLOK 2L
KEDOYA SELATAN, KEBON JERUK, JAKBAR

DATE: AUGUST 20, 2019

ATTN : ENDANG

SAMPLE DESCRIPTION:

THE SUBMITTED SAMPLE SAID TO BE:

SAMPLE DESCRIPTION : NUVRINO (Ikat, Viva, Solara)

TESTING STAGE : PRODUCTION SAMPLE

TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGES.

CONCLUSION:

TESTED SAMPLE

SUBMITTED SAMPLE

STANDARD


MOULD RESISTANCE TEST

- WITH REFERENCE TO ASTM G21-2015

RESULT

SEE TEST DATA

PREPARED AND CHECKED BY:
FOR INTERTEK INDONESIA



TAUFIQ URAKHMAN
HARDLINE LAB MANAGER

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>



TESTS CONDUCTED:

1. MOULD RESISTANCE TEST

With reference to ASTM G21-2015 Standard Practice for Determining Resistance of Synthetic Polymeric Materials to Fungi.

Test specimen : 2 X 2 INCH / 2 Inch Diameter / 26mm Long / grey surface of submitted sample.

Temperature of incubation : 28°C.

Mould culture used : *Aspergillus brasiliensis* (ATCC 9642), *Penicillium pinophilum* (ATCC 11797), *Chaetomium globosum* (ATCC 6205), *Gliocladium virens* (ATCC 9645) and *Aureobasidium pullulans* (ATCC 15233) with positive vitality.

<u>Sample</u>	<u>Rating* at the specific period of incubation (day)</u>
	<u>28th</u> 0(0%)

Tested component: Grey material.

Remark : *= Rating scale ranking from 0 to 4 and each number represents the degree of mould growth observed on the specimen surface.

- 0- None (no growth on specimen surface.)
- 1- Traces of growth (less than 10%).
- 2- Light growth (10%-30%).
- 3- Medium growth (30%-60%).
- 4- Heavy growth (60% to complete coverage).

Sample received condition: sample in closed plastic bag.

DATE SAMPLE RECEIVED : JULY 24, 2019
TESTING PERIOD : JULY 24, 2019 TO AUGUST 20, 2019


END OF REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>



PRODUCT PHOTO



The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>

**PT BERKAT UNGGUL PRATAMA
KOMPLEK CITTA GRAHA JL. PANJANG NO. 26
BLOK 2L, KEDOYA SELATAN, KEBON JERUK**

The following sample was (were) submitted and identified by the client as:

Sample No.	Sample Description
A	NUVRINO (Ikat, Viva, Solara), SYNTHETIC LEATHER, FABRIC WIDTH 137 CM, IN NV-2707 - COLOR

Client's reference No. : 1910010102
 Buyer : -
 Brand : -
 Style Number : -
 Season : -
 Thickness : -
 Lot : -
 End use : -
 Manufacturer : -
 Country of Origin : -
 Country of Destination : -
 Applicant's proposed care instructions : -
 Sample Receiving Date : JUNE 24, 2019
 Test Performing Period : JUNE 24 – JULY 11, 2019
 Test Results : Please refer to the next page(s).

Signed for and on behalf of
PT. SGS Indonesia



Ellya Santhy
Softlines & Toys Lab. Manager

This document is issued by the Company subject to its General Conditions of Service printed overleaf, or available on request or accessible at www.sgs.com/termsandconditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, Indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.
 Unless otherwise stated the results shown in this test report refer only to the sample(s) tested and such sample(s) are retained 30 days only.
WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction.
 The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted.

Test Result:

Colour Fastness To UV Exposure of Nonmetallic Materials^ (ASTM G154-2012a)

Exposure cycle:

Cycle 1 : 8 hours UV at 60(±3)□ BPT, 0.89 W/m²/nm @ 340nm
4 hours condensation at 50(±3)°C BPT

Specified Requirement

After 200 hour
Colour Change

4.5

/

Remarks : Grey Scale Rating is based on the 5-step scale of 1 to 5, where 1 is bad and 5 is good.

Remark^ = "The captioned test is conducted by SGS Hong Kong Ltd, test report number: SL119002566123TX, dated at July 11, 2019."

This document is issued by the Company subject to its General Conditions of Service printed overleaf, or available on request or accessible at www.sgs.com/termsandconditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.
Unless otherwise stated the results shown in this test report refer only to the sample(s) tested *and such sample(s) are retained 30 days only*.
WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction.

The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted.

Sample Picture



1910010102

*****End of Report*****

This document is issued by the Company subject to its General Conditions of Service printed overleaf, or available on request or accessible at www.sgs.com/termsandconditions.htm and for electronic format documents, subject to Terms and Conditions for Electronic Documents at www.sgs.com/terms_e-document.htm. Attention is drawn to the limitation of liability, indemnification and jurisdiction issues defined therein. Any holder of this document is advised that information contained hereon reflects the Company's findings at the time of its intervention only and within the limits of Client's instructions, if any. The Company's sole responsibility is to its Client and this document does not exonerate parties to a transaction from exercising all their rights and obligations under the transaction documents. This document cannot be reproduced except in full, without prior written approval of the Company. Any unauthorized alteration, forgery or falsification of the content or appearance of this document is unlawful and offenders may be prosecuted to the fullest extent of the law.

Unless otherwise stated the results shown in this test report refer only to the sample(s) tested *and such sample(s) are retained 30 days only.*

WARNING: The sample(s) to which the findings recorded herein (the "Findings") relate was(were) drawn and / or provided by the Client or by a third party acting at the Client's direction.

The Findings constitute no warranty of the sample's representativeness of any goods and strictly relate to the sample(s). The Company accepts no liability with regard to the origin or source from which the sample(s) is/are said to be extracted.

TEST REPORT

APPLICANT : PT BERKAT UNGGUL PRATAMA
KOMPLEK CITTA GRAHA
JL. PANJANG NO. 26 BLOK 2L, KEDOYA
SELATAN, KEBON JERUK, JAKARTA BARAT

DATE: FEBRUARY 27, 2023

ATTN : ENDANG MAWARNI S

THE SUBMITTED SAMPLE SAID TO BE:

SAMPLE DESCRIPTION : NUVRINO (Ikat, Viva, Solara)
COLORS : ALL COLORS
ORDER/STYLE NO. : ALL STYLE
BUYERS COMPANY NAME : PT BERKAT UNGGUL PRATAMA
COUNTRY OF DESTINATION : ALL COUNTRY
COUNTRY OF ORIGIN : TAIWAN
TESTING STAGE : PRODUCTION SAMPLE

TESTS CONDUCTED:

AS REQUESTED BY THE APPLICANT, FOR DETAILS REFER TO ATTACHED PAGES.

CONCLUSION:

<u>TESTED SAMPLE</u>	<u>STANDARD</u>	<u>RESULT</u>
SUBMITTED SAMPLE	ANTIBACTERIAL ACTIVITY TEST	SEE TEST CONDUCTED

REMARK :

Test was subcontracted to Intertek China.

PREPARED AND CHECKED BY:
FOR INTERTEK INDONESIA



TAUFIQ URAKHMAN
HARDLINE LAB MANAGER

RT/AK/YP/IS/DN/RM

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>



Tests Conducted:

1. Antibacterial Activity Test- Parallel Streak Method (Qualitative)

With reference to 2012 American Association of Textile Chemists and Colorists, Technical Manual, AATCC Test Method 147-2011.

Incubation temperature: 37°C.
Incubation period: 18 - 24 hours.
Agar medium: Nutrient agar.

Test culture: Staphylococcus aureus (ATCC 6538).
Klebsiella pneumoniae (ATCC 4352).

Test specimen: 25 X 50mm / rectangular / indicated surface of submitted sample.

Test Item	Result
	1
Staphylococcus aureus (ATCC 6538)	No growth was observed directly underneath the tested specimen.with *clearzone 6.8 mm.
Klebsiella pneumoniae (ATCC 4352)	No growth was observed directly underneath the tested specimen.with *clearzone1.7 mm.

* = Width of clear zone of inhibition belong the edge of the tested specimen.
Sample received condition: Sample in closed plastic bag.

Reference Rating^{##}:

Result	Anti-Bacterial Activity
Growth of test miroorganism was observed directly underneath the tested specimen	Not Acceptable
No growth of test miroorganism was observed directly underneath the tested specimen	Acceptable

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>



Test Conducted:

Comment:

Tested sample	Antibacterial activity (AATCC-147)	Result
Tested component of Submitted sample	Against Staphylococcus aureus	Acceptable
	Against Klebsiella pneumoniae	Acceptable

No.	Test Component Description(s)
(1)	NUVRINO (Ikat, Viva, Solara)

Date Sample Received : January 19, 2023
 Testing Period : January 19, 2023 to February 27, 2023


END OF REPORT

This report is made solely on the basis of your instructions and/or information and materials supplied by you. It is not intended to be a recommendation for any particular course of action. Intertek does not accept a duty of care or any other responsibility to any person other than the Client in respect of this report and only accepts liability to the Client insofar as is expressly contained in the terms and conditions governing Intertek's provision of services to you. Intertek makes no warranties or representations either express or implied with respect to this report save as provided for in those terms and conditions. We have aimed to conduct the Review on a diligent and careful basis and we do not accept any liability to you for any loss arising out of or in connection with this report, in contract, tort, by statute or otherwise, except in the event of our gross negligence or wilful misconduct.

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
 Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
 For the complete term and condition, please visit: <http://www.intertek.com/terms>



PRODUCT PHOTO



EXH 1

The report shall not be reproduced wholly or in parts without written approval of the laboratory.
Except where explicitly agreed in writing, all work and services performed by Intertek is subject to our General Terms and Conditions.
For the complete term and condition, please visit: <http://www.intertek.com/terms>



CARA PERAWATAN BAHAN KULIT SINTETIK

✓ DO's

Apa yang **HARUS** dilakukan



Gunakan lap basah (lembab)
berbahan lembut untuk
membersihkan permukaan bahan



Gosok permukaan bahan secara
perlahan dengan intens



Jika terkena noda dengan bahan
pewarna yang cukup intens, usahakan
untuk membersihkan bagian tersebut
dengan lap basah sesegera mungkin



Apabila ada noda yang masih tertinggal,
gunakan pembersih khusus untuk kulit
sintetik untuk membantu menghilangkan
noda tersebut

✗ DONT's

Apa yang **TIDAK BOLEH** dilakukan



Jangan gunakan bahan yang
kasar / tajam (seperti sikat) untuk
membersihkan permukaan kulit



Jangan gunakan produk pembersih
berbahan keras (kimia) seperti :
pemutih, deterjen, thinner, dll

Catatan:

Tinta pulpen, spidol permanen, bahan jeans dan material berwarna kuat lainnya kemungkinan besar akan sulit atau tidak bisa dibersihkan secara sempurna, terutama pada bahan kulit berwarna terang

